

Standard Tile Adhesive

Guide Formulation

Mineral base mixture	Parts by Weight
Portland cement	30- 40
Limestone flour < 0,1 mm	5- 10
Quartz or Limestone sand 0,1 - 0,4 mm	45- 60

Additives	Parts by Weight
KimaCell Cellulose ether	0,35-0,5
Redispersible Polymer powder	0,5- 1,5

Optimizing additives	Parts by Weight
Cellulose fibres < 0,4 mm	0,1 -0,3
High aluminat cement	1 -3
Calcium formate	0,4-0,8